

USE OF NON-FERROUS METALS IN CONTACT WITH BAL™ SEALS IN DYNAMIC SERVICE

Technical Report
TR-7 (Rev. A; 04-25-01)
(100-66)



19650 Pauling
Foothill Ranch, CA 92610-2610
Tel (949) 460-2100
Fax (949) 460-2300
Email: sales@balseal.com
www.balseal.com

Spinozastraat 1
1018 HD Amsterdam
The Netherlands
Tel +31 20 638 6523
Fax +31 20 625 6018
Email: sales@balseal.nl
www.balseal.nl

1.0 DISCUSSION

The type of material with which the seal comes in contact substantially affects the performance of BAL™ Seals. Non-ferrous materials are generally softer than heat treated steel materials and there will be a greater tendency for the BAL Seal to wear and in turn may abrade the metal surface coming in contact with the seal.

2.0 CONSIDERATION ON THE SELECTION OF METALLIC MATERIALS IN CONTACT WITH BAL™ SEALS DYNAMICALLY

The selection of the material in contact with the BAL Seals will depend on the following factors: cost, chemical compatibility, weight, and desirable mechanical properties. Generally, one feature will override the others.

MATERIAL	AVERAGE EQUIVALENT HARDNESS ROCKWELL C	CORROSION RESISTANCE	ABRASION TO BAL SEAL
Aluminum (Hard Anodize)	62	Low	High
Bronze	20 (approx.)	Good	Low
Brass	18 (free cutting)	Medium	Medium
Monel K500	26	Medium	Medium
Hastelloy C-276	41 (cold worked)	Good	High

3.0 MATERIAL SURFACE HARDNESS AND ITS EFFECT ON SEAL PERFORMANCE

In general, the harder the material with which the seal comes in contact, the lower the adhesion between the seal and the sealing surface and the lower the friction, which results in lower wear. BAL Seal Engineering Company, Inc. has seals that are designed for use in contact with soft materials. Hard anodizing, plating, and other processes may increase certain materials' surface hardness.

3.0 LUBRICATION AND WEAR

Lubrication, either wet or dry, tends to reduce the adhesion and coefficient of friction between two surfaces, which results in lower wear. In general, wet lubricants are superior to dry lubricants. However, dry lubricants have many advantages. Whenever possible, lubrication – wet or dry – should be used.

The information, descriptions, recommendations and opinions set forth herein are offered solely for your consideration, inquiry, and verification and are not, in part or in whole, to be construed as constituting a warranty, expressed or implied, nor shall they form or be a part of the basis of any bargain with Bal Seal Engineering. If any sample or model was shown to or provided by Buyer/User, such sample or model was used merely to illustrate the general description and type of goods. Such use is not to be construed as a warranty that the goods will conform to the sample or model. Furthermore, THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES, IMPLIED OR EXPRESSED, ARE EXCLUDED AND SHALL NOT APPLY. This document provides product options for further investigation by Buyers/Users having technical expertise. The Buyer/User, through its own analysis and testing, is solely responsible for making the final selection of the products and for assuming that all performance, safety and warning requirements for the application are met. It is recommended that Buyers/Users run evaluation testing under actual service conditions to determine whether proposed Bal Seal products are suitable for the intended purpose. Nothing contained herein or in any of our literature shall be considered a license or recommendation for any use that may infringe patent rights. (LE-17)

PATENTS: The items described in this report include products that are the subject of the following issued United States patents: 5,979,904; 5,994,856; 6,050,572; 5,984,316; 6,161,838 and others, as well as foreign patents or products where patents are pending. (LE-88G)

©Copyright 2001, Bal Seal Engineering Co., Inc. U.S.A.

Use or disclosure of data contained on this sheet is subject to the restrictions contained in the disclaimer.