

**COEFFICIENT OF THERMAL EXPANSION  
FOR VARIOUS MATERIALS  
AT DIFFERENT TEMPERATURES**

Technical Report  
TR-18 (Rev. F)



19650 Pauling  
Foothill Ranch, CA 92610-2610  
Tel (949) 460-2100  
Fax (949) 460-2300  
Email: [sales@balseal.com](mailto:sales@balseal.com)  
[www.balseal.com](http://www.balseal.com)

Bal Seal Engineering Europe B.V.  
Jollemanhof 16, 5th Floor  
1019 GW Amsterdam  
The Netherlands  
Tel +31 20 638 6523  
Fax +31 20 625 6018  
Email: [ordersbv@balseal.nl](mailto:ordersbv@balseal.nl)

---

## CONTENTS

- 1.0 Purpose
- 2.0 Scope
- 3.0 Definitions
- 4.0 Charts
- 5.0 Reference

It is essential that the customer run evaluation testing under actual service conditions with a sufficient safety factor to determine if the proposed, supplied, or purchased, Bal Seal Engineering products are suitable for the intended purpose and to confirm expected results. Bal Seal Engineering makes no warranty, express or implied, regarding Bal Seal Engineering products or of the information contained herein, including but not limited to, warranties of merchantability, performance, and fitness for a particular use or purpose. Bal Seal Engineering shall not be liable for any loss or damage of any kind or nature that may result from the use of, reference to, or reliance on, the information contained herein, including, but not limited to, consequential, special (including loss of profits) direct, indirect, incidental, or similar damages, even if Bal Seal Engineering has been advised of the possibility of such damages. (LE-173-2.4 Rev.Ø) TR-18 rev A 6/25/2004 RR 100-71-2)

## **Coefficient of Thermal Expansion for Various Materials at Different Temperatures**

---

### **1.0 Purpose**

The purpose of this Technical Report is to show the coefficient of thermal expansion (CTE) for various metallic and non-metallic materials used in springs and seals made by Bal Seal Engineering Co.

### **2.0 Scope**

The coefficient of thermal expansion is used to determine the rate at which a material expands as a function of temperature. CTE is used for design purposes to determine if failure by thermal stress may occur. Understanding the relative expansion/contraction characteristics of materials is important for application success.

The CTE values are of considerable interest to design engineers. Plastics tend to expand and contract anywhere from six to nine times more than metals. The thermal expansion difference develops internal stresses and stress concentrations in the polymer, which allows premature failure to occur.

### **3.0 Definition**

The coefficient of thermal expansion is defined as the change in length or volume of a material for a unit change in temperature. The overall coefficient is the linear thermal expansion (in.) per degree Fahrenheit or Celsius. The CTE data is calculated by the change in length divided by the quantity of the length at room temperature, multiplied by the change of temperature.

## Coefficient of Thermal Expansion for Various Materials at Different Temperatures

### 4.0 Charts

#### 4.1 Chart 1

Metals  
inch / inch / deg F  
(mm / mm / deg C)

STEELS								
	32° to 600°F	(0° to 316°C)	32° to 400°F	(0° to 205°C)	32° to 200°F	(0° to 93°C)	32° to -100°F	(0° to -73°C)
303 SS	9.9 x 10 <sup>-6</sup>	(17.8 x 10 <sup>-6</sup> )			9.6 x 10 <sup>-6</sup>	(17.3 x 10 <sup>-6</sup> )	9.3 x 10 <sup>-6</sup>	(16.7 x 10 <sup>-6</sup> )
304 SS	9.4 x 10 <sup>-6</sup>	(16.9 x 10 <sup>-6</sup> )	9.2 x 10 <sup>-6</sup>	(16.6 x 10 <sup>-6</sup> )	8.8 x 10 <sup>-6</sup>	(15.8 x 10 <sup>-6</sup> )	8.2 x 10 <sup>-6</sup>	(14.8 x 10 <sup>-6</sup> )
347 SS	9.5 x 10 <sup>-6</sup>	(17.1 x 10 <sup>-6</sup> )	9.4 x 10 <sup>-6</sup>	(16.9 x 10 <sup>-6</sup> )	9.3 x 10 <sup>-6</sup>	(16.7 x 10 <sup>-6</sup> )	8.5 x 10 <sup>-6</sup>	(15.3 x 10 <sup>-6</sup> )
410 SS	5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )			5.5 x 10 <sup>-6</sup>	(9.9 x 10 <sup>-6</sup> )		
416 SS	5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )			5.5 x 10 <sup>-6</sup>	(9.9 x 10 <sup>-6</sup> )		
440 SS	5.9 x 10 <sup>-6</sup>	(10.6 x 10 <sup>-6</sup> )			5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )	5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )
13-8 PH SS							5.8 x 10 <sup>-6</sup>	(10.4 x 10 <sup>-6</sup> )
15-5 PH SS			6.0 x 10 <sup>-6</sup>	(10.8 x 10 <sup>-6</sup> )	6.0 x 10 <sup>-6</sup>	(10.8 x 10 <sup>-6</sup> )	5.8 x 10 <sup>-6</sup>	(10.4 x 10 <sup>-6</sup> )
17-4 PH SS Condition A	6.2 x 10 <sup>-6</sup>	(11.2 x 10 <sup>-6</sup> )	6.0 x 10 <sup>-6</sup>	(10.8 x 10 <sup>-6</sup> )	6.0 x 10 <sup>-6</sup>	(10.8 x 10 <sup>-6</sup> )		
17-4 PH SS Condition H900	6.3 x 10 <sup>-6</sup>	(11.3 x 10 <sup>-6</sup> )	6.1 x 10 <sup>-6</sup>	(11.0 x 10 <sup>-6</sup> )	6.0 x 10 <sup>-6</sup>	(10.8 x 10 <sup>-6</sup> )		
17-7 PH SS Condition A	9.5 x 10 <sup>-6</sup>	(17.1 x 10 <sup>-6</sup> )	9.0 x 10 <sup>-6</sup>	(16.2 x 10 <sup>-6</sup> )	8.5 x 10 <sup>-6</sup>	(15.3 x 10 <sup>-6</sup> )		
17-7 PH Condition H900	6.4 x 10 <sup>-6</sup>	(11.5 x 10 <sup>-6</sup> )	6.3 x 10 <sup>-6</sup>	(11.3 x 10 <sup>-6</sup> )	6.1 x 10 <sup>-6</sup>	(11.0 x 10 <sup>-6</sup> )		
A286 SS	9.8 x 10 <sup>-6</sup>	(17.6 x 10 <sup>-6</sup> )	9.4 x 10 <sup>-6</sup>	(16.9 x 10 <sup>-6</sup> )	9.2 x 10 <sup>-6</sup>	(16.6 x 10 <sup>-6</sup> )		
1020 CRS	7.0 x 10 <sup>-6</sup>	(12.6 x 10 <sup>-6</sup> )	7.0 x 10 <sup>-6</sup>	(12.6 x 10 <sup>-6</sup> )	7.0 x 10 <sup>-6</sup>	(12.6 x 10 <sup>-6</sup> )		
4140 High Alloy Steel			13.7 x 10 <sup>-6</sup>	(24.7 x 10 <sup>-6</sup> )	12.7 x 10 <sup>-6</sup>	(22.9 x 10 <sup>-6</sup> )		
4340 High Alloy Steel			13.6 x 10 <sup>-6</sup>	(24.5 x 10 <sup>-6</sup> )	12.4 x 10 <sup>-6</sup>	(22.3 x 10 <sup>-6</sup> )		
H13 Tool Steel			11.5 x 10 <sup>-6</sup>	(20.7 x 10 <sup>-6</sup> )				
H11 Tool Steel			11.5 x 10 <sup>-6</sup>	(20.7 x 10 <sup>-6</sup> )				
Vasco T-250	5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )						
Tungsten Carbide K801			2.7 x 10 <sup>-6</sup>	(4.9 x 10 <sup>-6</sup> )			2.2 x 10 <sup>-6</sup>	(3.9 x 10 <sup>-6</sup> )

## Coefficient of Thermal Expansion for Various Materials at Different Temperatures

ALUMINUM AND OTHER ALLOYS								
	68° to 392°F	(20° to 202°C)	68° to 212°F	(20° to 100°C)	68° to -58°F	(20° to -50°C)	68° to -238°F	(20° to -150°C)
<b>356</b>	12.5 x 10 <sup>-6</sup>	(22.5 x 10 <sup>-6</sup> )	11.9 x 10 <sup>-6</sup>	(21.4 x 10 <sup>-6</sup> )	11.0 x 10 <sup>-6</sup>	(19.8 x 10 <sup>-6</sup> )		
<b>2014</b>	13.1 x 10 <sup>-6</sup>	(23.6 x 10 <sup>-6</sup> )	12.5 x 10 <sup>-6</sup>	(22.5 x 10 <sup>-6</sup> )	12.0 x 10 <sup>-6</sup>	(21.6 x 10 <sup>-6</sup> )	10.9 x 10 <sup>-6</sup>	19.6 x 10 <sup>-6</sup>
<b>2024</b>	13.2 x 10 <sup>-6</sup>	(23.8 x 10 <sup>-6</sup> )	12.6 x 10 <sup>-6</sup>	(22.7 x 10 <sup>-6</sup> )	11.9 x 10 <sup>-6</sup>	(21.4 x 10 <sup>-6</sup> )	10.8 x 10 <sup>-6</sup>	(19.4 x 10 <sup>-6</sup> )
<b>6061</b>	13.5 x 10 <sup>-6</sup>	(24.3 x 10 <sup>-6</sup> )	13.0 x 10 <sup>-6</sup>	(23.4 x 10 <sup>-6</sup> )	12.1 x 10 <sup>-6</sup>	(21.8 x 10 <sup>-6</sup> )		
<b>7075</b>	13.5 x 10 <sup>-6</sup>	(24.3 x 10 <sup>-6</sup> )	12.9 x 10 <sup>-6</sup>	(23.2 x 10 <sup>-6</sup> )	12.1 x 10 <sup>-6</sup>	(21.8 x 10 <sup>-6</sup> )		
<b>Magnesium</b>			14.4 x 10 <sup>-6</sup>	(25.9 x 10 <sup>-6</sup> )				
<b>Aluminum Si-Bronze</b>			16.6 x 10 <sup>-6</sup>	(29.9 x 10 <sup>-6</sup> )	9.0 x 10 <sup>-6</sup>	(16.2 x 10 <sup>-6</sup> )	8.1 x 10 <sup>-6</sup>	(14.6 x 10 <sup>-6</sup> )
<b>Titanium 6AL-4V</b>	5.0 x 10 <sup>-6</sup>	(9.0 x 10 <sup>-6</sup> )	4.8 x 10 <sup>-6</sup>	(8.6 x 10 <sup>-6</sup> )			1.3 x 10 <sup>-6</sup>	(2.3 x 10 <sup>-6</sup> )

4.2 Chart 2      Plastics and other non-metals  
 inch / inch / deg F  
 (mm / mm / deg C)

PTFE AND PTFE BAL SEAL COMPOSITIONS								
	77° to 572°F	(25° to 300°C)	77° to 392°F	(25° to 202°C)	77° to 212°F	(25° to 100°C)	77° to -58°F	(25° to -50°C)
<b>PTFE (plain)</b>					79.6 x 10 <sup>-6</sup>	(143.3 x 10 <sup>-6</sup> )		
<b>G (Graphite PTFE)</b>					78.5 x 10 <sup>-6</sup>	(141.3 x 10 <sup>-6</sup> )		
<b>GC (Graphite-Carbon PTFE)</b>					76.2 x 10 <sup>-6</sup>	(137.2 x 10 <sup>-6</sup> )		
<b>GFPA (Graphite-fiber-reinforced PTFE)</b>					70.3 x 10 <sup>-6</sup>	(126.7 x 10 <sup>-6</sup> )		
<b>GL-20</b>					76.8 x 10 <sup>-6</sup>	(132.2 x 10 <sup>-6</sup> )		
<b>SP-31 (Polymer-Filled PTFE)</b>					77.2 x 10 <sup>-6</sup>	(139.0 x 10 <sup>-6</sup> )		

POLYMERS AND OTHER NON-METALLIC MATERIALS								
Halar			54.0 x 10 <sup>-6</sup>	(97.2 x 10 <sup>-6</sup> )	44.0 x 10 <sup>-6</sup>	(79.2 x 10 <sup>-6</sup> )		
Polyimide			78.0 x 10 <sup>-6</sup>	(140.4 x 10 <sup>-6</sup> )				
Tefzel					52.0 x 10 <sup>-6</sup>	(93.6 x 10 <sup>-6</sup> )		
Torlon Virgion Type 4203					17.0 x 10 <sup>-6</sup>	(30.6 x 10 <sup>-6</sup> )		
Torlon w/30% Graphite Type 4301					5.6 x 10 <sup>-6</sup>	(10.1 x 10 <sup>-6</sup> )		
Vespel SP-1 Virgin	30.0 x 10 <sup>-6</sup>	(54.0 x 10 <sup>-6</sup> )					25.0 x 10 <sup>-6</sup>	(45.0 x 10 <sup>-6</sup> )
Vespel SP-21	23.0 x 10 <sup>-6</sup>	(41.4 x 10 <sup>-6</sup> )					25.0 x 10 <sup>-6</sup>	(45.0 x 10 <sup>-6</sup> )
Nylon					50.0 x 10 <sup>-6</sup>	(90.0 x 10 <sup>-6</sup> )		
Silicone Rubber			190.0 x 10 <sup>-6</sup>	(342.0 x 10 <sup>-6</sup> )				
Mech. Carbons	1.2 to 2.5 x 10 <sup>-6</sup>	(2.16 to 4.5 x 10 <sup>-6</sup> )						

## Coefficient of Thermal Expansion for Various Materials at Different Temperatures

---

### 5.0 References

#### 5.1 Conversion Factors:

Degrees Fahrenheit = ( $^{\circ}\text{C} \times 1.8$ ) + 32

Degrees Rankine = Degrees Fahrenheit + 459.7

Degrees Centigrade =  $(\text{F} - 32) / 1.8$

Degrees Kelvin = Degrees Centigrade + 273

#### 5.2 Bal Seal Report -RMS-41 Fluoropolymers, UHMW Polyethylene and Other Plastics as Seal Materials

#### 5.3 LNP Engineering Plastics [www.lnp.com](http://www.lnp.com)