



Polyester Elastomer (ER72)

Material Data Sheet
M-74 (Rev. 00; 08-18-20)

19650 Pauling
Foothill Ranch, CA
USA 92610-2610
O +1 949 460 2100
F +1 949 460 2300

VIDA Building, 1st floor
Kabelweg 57
1014 BA Amsterdam
The Netherlands
O +31 20 638 6523
F +31 20 625 6018

Suite 901, Chinachem
Century Tower
178 Gloucester Road,
Wanchai, Hong Kong
O +852 28681860
F +852 22956753

www.balseal.com



Overview

ER72 is a polyester elastomer with high flexibility and conformance properties and excellent sealing effectiveness. It is often chosen for sealing applications where surface finish is poor and surface irregularities prevent the use of materials with a lower degree of elasticity.

In addition, ER72 is used in moist or wet food contact applications where a high degree of chemical compatibility is needed. This material has low abrasion to soft mating parts, and is suitable for sealing moist environments and aqueous solutions at low speeds.

ER72 is recommended for use in temperatures from -320°F to $+475^{\circ}\text{F}$ (-196°C to $+246^{\circ}\text{C}$).

Chemical Compatibility

ER72 has excellent chemical compatibility. This material is compatible with most fluids and gases, but it is not recommended for use with sulfuric and nitric acids, alkali metals, chlorine fluoride, lithium, potassium, and sodium at high temperatures.

Compliance

ER72 is made from FDA compatible and compliant resins and materials. SP191 is a composition which contains ingredients that meet FDA regulation 21 CFR 170.39 for use in food contact applications. Bal Seal Engineering defines its compositions as "FDA Compliant" if each of the ingredients in the composition have been found by the FDA to be "safe for use in food contact," or "acceptable for use in food contact."

Color

Tan

Mechanical Properties of ER72

Tensile Strength (typical)	Elongation (typical)	Hardness (typical)
6650 psi	360%	72 ShoreD (54 Rc)

Advantages

- Low abrasion to soft materials
- Can conform to irregular surfaces
- High compatibility with chemicals and abrasive particles

Application Examples

- Welding equipment seals
- Electronics/semiconductor equipment
- Sensors

Other Information

For more information, contact a technical sales representative, or e-mail us at solutions@balseal.com

The information, descriptions, recommendations and opinions set forth herein are offered solely for your consideration, inquiry, and verification and are not, in part or in whole, to be construed as constituting a warranty, expressed or implied, nor shall they form or be a part of the basis of any bargain with Bal Seal Engineering, Inc.. If any sample or model was shown to or provided by Buyer/User, such sample or model was used merely to illustrate the general description and type of goods. Such use is not to be construed as a warranty that the goods will conform to the sample or model. Furthermore, THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES, IMPLIED OR EXPRESSED, ARE EXCLUDED AND SHALL NOT APPLY. This document provides product options for further investigation by Buyers/Users having technical expertise. The Buyer/User, through its own analysis and testing, is solely responsible for making the final selection of the products and for assuming that all performance, safety and warning requirements for the application are met. It is recommended that Buyers/Users run evaluation testing under actual service conditions to determine whether proposed Bal Seal Engineering products are suitable for the intended purpose. Nothing contained herein or in any of our literature shall be considered a license or recommendation for any use that may infringe patent rights. (LE-17)