



Polyimide-Filled Polytetrafluoroethylene (SP191)

Material Data Sheet
M-64 (Rev. 02; 08-18-20)

19650 Pauling
Foothill Ranch, CA
USA 92610-2610
O +1 949 460 2100
F +1 949 460 2300

VIDA Building, 1st floor
Kabelweg 57
1014 BA Amsterdam
The Netherlands
O +31 20 638 6523
F +31 20 625 6018

Suite 901, Chinachem
Century Tower
178 Gloucester Road,
Wanchai, Hong Kong
O +852 28681860
F +852 22956753

www.balseal.com



Overview

SP191 is a polyimide-filled PTFE compound which exhibits low friction and minimal wear in rotary and reciprocating sealing applications. SP191 performs well against soft mating surfaces such as aluminum, mild steel, brass, and plastics, and it is ideal for use in stop-start applications where the goal is to eliminate stick-slip. SP191 demonstrates exceptional resistance against gas permeability, and is often used when optimal sealing of gases is desired. This material is suggested for use in applications with service temperatures ranging from -400°F to 550°F (-240°C to 287°C).

Chemical Compatibility

SP191 exhibits excellent compatibility with most fluids and gases. For more details, reference Technical Report 60A, "Chemical Compatibility Guide," in the technical library section of our website at www.balseal.com.

SP191 can be repeatedly sterilized using conventional EtO method without loss of biocompatibility or degradation of mechanical properties.

SP191 can be repeatedly sterilized using conventional autoclave method (steam) without loss of biocompatibility or degradation of mechanical properties.

Compliance

SP191 is a pre-qualified material for medical, pharmaceutical, and implantable applications per Bal Seal Engineering. Bal Seal Engineering defines a medical, pharmaceutical, and implantable material as a composition that meets ISO 10993-5 (cytotoxicity) and USP Class VI requirements as tested by a qualified third party.

SP191 is a composition which contains ingredients that meet FDA regulation 21 CFR 170.39 for use in food contact applications. Bal Seal Engineering defines its compositions as "FDA Compliant" if each of the ingredients in the composition have been found by the FDA to be "safe for use in food contact," or "acceptable for use in food contact."

SP191 is a low-outgassing material per ASTM E595. ASTM E595 defines low-outgassing materials as materials that have a Total Mass Loss (TML) of less than 1% and Collected Volatile Condensable Materials (CVCM) of less than 0.1%.

Color

Tan (color variations may occur during processing)

Heat Treatment

Certain seal sizes are supplied as SP191 HT where HT stands for a heat treatment to limit dimensional changes. Material properties and composition remain the same.

Mechanical Properties of SP191

Tensile Strength (typical)	Elongation (typical)	Hardness (typical)
2800 psi	225%	59 ShoreD (45 Rc)

Applications

- Industrial robotics
- HPLC pumps
- Surgical tools
- Medical equipment
- Aerospace gimbals/pods/pan-tilt systems

Other Information

For more information, contact a technical sales representative, or e-mail us at solutions@balseal.com

The information, descriptions, recommendations and opinions set forth herein are offered solely for your consideration, inquiry, and verification and are not, in part or in whole, to be construed as constituting a warranty, expressed or implied, nor shall they form or be a part of the basis of any bargain with Bal Seal Engineering, Inc. If any sample or model was shown to or provided by Buyer/User, such sample or model was used merely to illustrate the general description and type of goods. Such use is not to be construed as a warranty that the goods will conform to the sample or model. Furthermore, THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES, IMPLIED OR EXPRESSED, ARE EXCLUDED AND SHALL NOT APPLY. This document provides product options for further investigation by Buyers/Users having technical expertise. The Buyer/User, through its own analysis and testing, is solely responsible for making the final selection of the products and for assuming that all performance, safety and warning requirements for the application are met. It is recommended that Buyers/Users run evaluation testing under actual service conditions to determine whether proposed Bal Seal Engineering products are suitable for the intended purpose. Nothing contained herein or in any of our literature shall be considered a license or recommendation for any use that may infringe patent rights. (LE-17)